



Co-Extruded Multi-Polymer Protective Tapes

2A25 • 2A26 • 2A29 (Clear)

Technical Data

August, 2004

Product Description 3M™ Co-Extruded Multi-Polymer Protective Tapes 2A25, 2A26 and 2A29 have a medium-tack adhesive system to help provide temporary protection for a variety of surface protection applications.

Product Construction	Backing	Adhesive	Colors	Standard Roll Size
	Multi-polymer*	Acrylic	Clear**	48 in. (1200 mm), 60 in. (1500 mm), 72 in. (1800 mm) x 1000 ft. (304.8 m) to 5000 ft. (1524 m)

*Resins used in the construction of the film backing are proprietary.

**Contact your local 3M representative for additional information on colors.

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

	Nominal Results			ASTM Test Method
Adhesion to Steel: (oz./in. width)	3M tape 2A25 6	3M tape 2A26 9	3M tape 2A29 10	D-3330
Tack Level:	Moderate	Moderate	Moderate	
Tensile Strength: (Break or Yield)	4500 PSI / 3.1 MPA			D-882
Elongation: (Break or Yield)	600%			D-882
Total Tape Thickness:	2.0 mils (0.05 mm)			D-3652

Features

- Medium-tack adhesive which will not lift during forming to help save money on reworks.
- Acrylic adhesive is non-corrosive, non-staining with stable performance and clean removal to help reduce labor costs.
- Heat resistance to withstand temperatures up to 160°F (71°C), approximately 30°F higher than conventional 3-mil LDPE tapes to help reduce reworks.
- Enhanced conformability to products which are subjected to severe forming or fabrication to help reduce reworks.
- Increased break strength for easier removability without tearing or slivering to help reduce labor costs.

3M™ Co-Extruded Multi-Polymer Protective Tapes

2A25 • 2A26 • 2A29 (Clear)

Application Ideas

- Automotive – urethane moldings, trim fascias and bumpers.
- Metals – aluminum: mill finish sheets and coils, skin quality and painted aluminum extrusions; stainless steel: 304 #3 finish.
- Architectural Panels and Garage Doors – embossed painted-gloss.
- General – decorative laminates.

Application Techniques

For optimum performance, these tapes should be applied and removed at a temperature not less than 60°F (16°C) and avoid prolonged exposure to direct UV sunlight which may affect the performance of the tape.

Storage

Store under normal conditions of 60° to 80°F (16° to 27°C) and 40 to 60% R.H. in the original carton.

Shelf Life

To obtain best performance, use these products within 12 months from date of manufacture.

3M™ Co-Extruded Multi-Polymer Protective Tapes

2A25 • 2A26 • 2A29 (Clear)

For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-241-2031 or 828-465-3053. Address correspondence to: 3M/PolyMask, 500 Thornburg Dr., P.O. Box 309, Conover, NC 28613. Our fax number is 1-800-672-3038 or 828-465-2404.

Product Use

All statements, technical information and recommendations contained in this document are based upon tests or experience that PolyMask Corporation and 3M believe are reliable. However, many factors beyond the control of PolyMask Corporation and 3M can affect the use and performance of a PolyMask Corporation product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the PolyMask Corporation product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Warranty and Limited Remedy

Unless stated otherwise in other product literature, packaging inserts or product packaging for individual products, PolyMask Corporation warrants that each PolyMask Corporation product meets the applicable specifications at the time PolyMask Corporation ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. **POLYMASK CORPORATION AND 3M COMPANY MAKE NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE.** User is responsible for determining whether the PolyMask Corporation product is fit for a particular purpose and suitable for user's application. If the PolyMask Corporation product is defective within the warranty period, your exclusive remedy and PolyMask Corporation's sole obligation will be, at PolyMask Corporation's option, to replace the product or refund the purchase price.

Limitation of Liability

Except where prohibited by law, 3M Company and PolyMask Corporation will not be liable for any loss or damage arising from the PolyMask Corporation product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2000

This product was manufactured under a quality system registered to ISO 9001:2000 standards by PolyMask Corporation, a joint venture of 3M and Sealed Air Corporation, and is sold by PolyMask Corporation with 3M acting as the sales representative of PolyMask Corporation.



Industrial Business Industrial Adhesives and Tapes Division

3M Center, Building 21-1W-10, 900 Bush Avenue
St. Paul, MN 55144-1000
www.3M.com/protectivetapes



Recycled Paper
40% pre-consumer
10% post-consumer

"3M" is a trademark of 3M Company used under license by PolyMask Corporation.
Printed in U.S.A.
©3M 2004 70-0709-4564-0 (8/04)